



# Prime Impax 450

## Prime Impax 450:

*Is our formulated High Impact Polystyrene. It provides good toughness, stiffness and impact strength. It is designed to meet a wide variety of product applications. Prime Impax 450 is one of the most versatile and inexpensive materials we supply. It is our standard thermoforming grade of High Impact Polystyrene.*

## Applications:

*Prime Impax 450 is FDA approved. Some applications include signs, credit cards, medical packaging, building products, displays, furniture and computer products. With a GP styrene cap it is also ideal for wall surrounds, bathtubs and other interior applications such as cabinet drawer silverware holders.*

## Processing:

*Since it is an amorphous thermoplastic material it is relatively easy to process in extrusion and thermoforming. The mold shrink is .003 - .006 in./in. It can be formed on aluminum, ceramic, fiberglass, epoxy and even wood tools.*



Prime Impax 450	Very High	High	Average
Impact Strength		*	
Low Temperature Impact Strength			*
Tensile Strength		*	
Flexural Modulus		*	
Heat Deflection Temperature			*



A Subsidiary of ICC Industries, Inc.

# Prime Impax 450

## Finishing:

*Prime Impax 450 can be fabricated by drilling, routing, sawing, die cut and/or laser cutting. Mechanical fasteners may be used as well as chemical bonding and sonic welding. We provide Prime Impax 450 in sheet or roll stock and are capable of holding extremely tight tolerances by either square cutting or slitting.*

*Please contact your Primex Plastics representative for more information on finishing, fabricating, or the thermoforming process.*

## Colors, Textures and Capabilities:

*Prime Impax 450 can be color matched to meet your specific requirements. It is offered in thicknesses of .010 - .400 and widths of up to 120". Textures available include; smooth, matte, Seville, RM, HC, Calf Grain, Levant, FL/HC and even flocked. Silicone coating, anti-stat, UVI and protective masking are also available.*

Property	Test Method	Value	Unit
Specific Gravity	D-792	1.04	
Melt Flow	D-1238	2.5	g/10min
Tensile @ Yield	D-638	2900	psi
Tensile Modulus	D-638	275,000	psi
Elongation @ Break	D-638	70	%
Flexural Modulus	D-790	300,000	psi
Notched Izod @ 73°F	D-256	2.1	ft-lb/in
HDT @ 264 psi	D-648	183	°F
Vicat Softening Point	D-1525	210	°F

Complies with UL 94 HB at thickness >.039 in.

Notice: All statements, information, and data given herein are believed to be accurate and reliable but are presented without guarantee, warranty, or responsibility of any kind, expressed or implied. Statements or suggestions concerning possible use of our products are made without representation of warranty that such use is free of patent infringement and are not recommendations to infringe any patent. The user should not assume that all safety measures are indicated, or that other measures may not be required.

[www.primexplastics.com](http://www.primexplastics.com)